



ALLSTATE GASKET MATERIAL SPECIFICATIONS

STYLE 1202 URETHANE SHEETING

Color: Various available

Recommended Uses:

- Available in full rolls and trimmed sheets
- Can be supplied in cut-to-width strips
- Pressure sensitive adhesive backing is also available
- Sizes vulcanized to infinity

Operating Temperature:

-40°F to 250°F

Typical Physical Properties				
Durometer	90A	80A	70A	60A
50% Modulus (psi)	-	-	-	140
100% Modulus psi (mPa)	1100	780	310	265
300% Modulus psi (mPa)	2200	1150	500	615
Tensile psi (mPa)	5500	5240	5400	4500
Elongation (%)	430	620	650	460
Tear - Die C, pli (kN/m)	600	420	300	168
- D-470, pli (kN/m)	-	98	-	30
Bashore Resilience (%)	42	23	30	8
Compression Set, Method B, 22hrs @ 158°F (70 C), %	25	59	31	(@78°F)
Compression Modulus, psi, 10% Deflection	-	-	-	3.2
Specific Gravity	1.1	-	1.25	-